



INTERNATIONAL APPLICATION PUBLISHED UNDER THE PATENT COOPERATION TREATY (PCT)

(51) International Patent Classification ⁶ : C08F 4/642, 10/00	A1	(11) International Publication Number: WO 99/21896 (43) International Publication Date: 6 May 1999 (06.05.99)
(21) International Application Number: PCT/EP98/06733 (22) International Filing Date: 23 October 1998 (23.10.98) (30) Priority Data: 97203331.0 29 October 1997 (29.10.97) EP (71) Applicant (for all designated States except US): MONTELL TECHNOLOGY COMPANY BV [NL/NL]; Hoeksteen 66, NL-2132 MS.Hoofddorp (NL). (72) Inventors; and (75) Inventors/Applicants (for US only): VAN BAAR, Jan, F. [NL/NL]; De Terp 45, NL-1911 AB Uitgeest (NL). GAL- IMBERTI, Maurizio [IT/IT]; Via Vertoiba, 4, I-20137 Mi- lano (IT). VON HEBEL, Klaas, L. [NL/NL]; Bernard van Beeklaan 40, NL-1241 AH Kortenhoef (NL). HORTON, Andrew, D. [GB/NL]; Titiaanstraat 1, NL-1077 RC Amster- dam (NL). VAN KESSEL, Gerard, M., M. [NL/NL]; Kon- ingsspil 6, NL-4191 TB Geldermalsen (NL). SCHUT, Pe- ter, A. [NL/NL]; Forelstraat 26, NL-1317 PT Almere (NL). DALL'OCCHO, Tiziano [IT/IT]; Via E. Farolfi, 3, I-44100 Ferrara (IT). (74) Agent: ZANOLI, Enrico; Montell Italia S.p.A., Via Pergolesi, 25, I-20124 Milano (IT).	(81) Designated States: AU, BR, CA, CN, CZ, HU, ID, IL, JP, KR, MX, NO, PL, RU, SG, TR, US, European patent (AT, BE, CH, CY, DE, DK, ES, FI, FR, GB, GR, IE, IT, LU, MC, NL, PT, SE). Published <i>With international search report.</i> <i>Before the expiration of the time limit for amending the</i> <i>claims and to be republished in the event of the receipt of</i> <i>amendments.</i>	
(54) Title: CATALYSTS FOR THE POLYMERIZATION OF OLEFINS AND PROCESS FOR THE PREPARATION THEREOF		
(57) Abstract <p>Catalysts for the polymerization of olefins are disclosed, comprising the product obtainable by contacting: (A) a bridged and/or substituted cyclopentadienyl compound of Ti, Zr or Hf; (B) one or more organometallic aluminium compounds of formula (II): $AlR^4_{3-z}H_z$ wherein the substituents R^4, same or different from each other, are linear or branched, saturated or unsaturated C_1-C_{20} alkyl or alkylaryl radicals, optionally containing Si or Ge atoms, wherein at least one of the substituents R^4 is different from a straight alkyl group; z is 0 or 1; and (C) water; the molar ratio between the organometallic aluminium compound and water being comprised between 1:1 and 100:1; said catalyst being obtainable by a process comprising the following steps: (i) contacting component (A) with part of component (B) in the absence of component (C); (ii) contacting part of component (B) with component (C) in the absence of component (A) and successively (iii) contacting the products obtained in steps (i) and (ii).</p>		

FOR THE PURPOSES OF INFORMATION ONLY

Codes used to identify States party to the PCT on the front pages of pamphlets publishing international applications under the PCT.

AL	Albania	ES	Spain	LS	Lesotho	SI	Slovenia
AM	Armenia	FI	Finland	LT	Lithuania	SK	Slovakia
AT	Austria	FR	France	LU	Luxembourg	SN	Senegal
AU	Australia	GA	Gabon	LV	Latvia	SZ	Swaziland
AZ	Azerbaijan	GB	United Kingdom	MC	Monaco	TD	Chad
BA	Bosnia and Herzegovina	GE	Georgia	MD	Republic of Moldova	TG	Togo
BB	Barbados	GH	Ghana	MG	Madagascar	TJ	Tajikistan
BE	Belgium	GN	Guinea	MK	The former Yugoslav Republic of Macedonia	TM	Turkmenistan
BF	Burkina Faso	GR	Greece	ML	Mali	TR	Turkey
BG	Bulgaria	HU	Hungary	MN	Mongolia	TT	Trinidad and Tobago
BJ	Benin	IE	Ireland	MR	Mauritania	UA	Ukraine
BR	Brazil	IL	Israel	MW	Malawi	UG	Uganda
BY	Belarus	IS	Iceland	MX	Mexico	US	United States of America
CA	Canada	IT	Italy	NE	Niger	UZ	Uzbekistan
CF	Central African Republic	JP	Japan	NL	Netherlands	VN	Viet Nam
CG	Congo	KE	Kenya	NO	Norway	YU	Yugoslavia
CH	Switzerland	KG	Kyrgyzstan	NZ	New Zealand	ZW	Zimbabwe
CI	Côte d'Ivoire	KP	Democratic People's Republic of Korea	PL	Poland		
CM	Cameroon	KR	Republic of Korea	PT	Portugal		
CN	China	KZ	Kazakstan	RO	Romania		
CU	Cuba	LC	Saint Lucia	RU	Russian Federation		
CZ	Czech Republic	LI	Liechtenstein	SD	Sudan		
DE	Germany	LK	Sri Lanka	SE	Sweden		
DK	Denmark	LR	Liberia	SG	Singapore		
EE	Estonia						

"CATALYSTS FOR THE POLYMERISATION OF OLEFINS AND PROCESS FOR THE PREPARATION THEREOF."


The present invention relates to catalysts for the polymerisation of olefins. In particular, it relates to high activity catalysts for the polymerisation of olefins obtained from cyclopentadienyl compounds of a transition metal, organometallic aluminium compounds and water.

The invention also relates to processes for the polymerisation of olefins carried out in the presence of the catalysts of the invention.

Homogeneous catalytic systems based on metallocene compounds, aluminium alkyl compounds and water are known to be active in the polymerisation of olefins.


In European Patent Application EP 384,171, catalysts for the polymerisation of olefins are described which comprise the reaction product of:

- (a) a metallocene compound of formula:



wherein $(C_5R'_n)$ is an optionally substituted cyclopentadienyl group and two or four R' substituents of one and the same cyclopentadienyl group can form one or two rings having 4 to 6 carbon atoms; R'' is a divalent radical bridging the two cyclopentadienyl groups; X can be for instance an halogen atom; M is a transition metal selected from Ti, Zr and Hf; p is 0 or 1; m is 0, 1 or 2, and when $m=0$ then $p=0$; and when $p=0$ at least one R' substituent is different from hydrogen; $n=4$ when $p=1$, and $n=5$ when $p=0$; and

- (b) an alumoxane of the formula:




wherein the substituents R can generically be alkyl, alkenyl or alkylaryl radicals, having 2-20 carbon atoms.

The alumoxanes (b) are prepared by reacting the corresponding trialkylaluminium compounds with water in a molar ratio of 2:1. In the alumoxanes used in the embodiment examples, the R substituents are isobutyl or 2-methylpentyl groups.


European Patent Application EP 575,875 describes homogeneous catalytic systems for the polymerisation of olefins comprising:

- (A) a cyclopentadienyl compound of formula:



in which M is Ti, Zr or Hf; $C_5R^1_{x-m}H_{5-x}$ and $C_5R^1_{y-m}H_{5-y}$ are equally or differently substituted cyclopentadienyl rings and two or four substituents R^1 of the same cyclopentadienyl group can form one or two rings, having from 4 to 6 carbon atoms; R^2 is a bridging group which links the two cyclopentadienyl rings; the substituents Q are preferably chlorine atoms; m can be 0 or 1; n can be 0 or 1, being 1 when m=1; x is an integer comprised between m+1 and 5; y is an integer comprised between m and 5;

- (B) an organometallic aluminium compound of formula:




wherein the substituents R^4 are alkyl, alkenyl or alkylaryl radicals, containing from 1 to 10 carbon atoms, which may also contain Si or Ge atoms, at least one of the substituents R^4 being different from a straight alkyl group; z is 0 or 1; and

- (C) water.

The molar ratio between the organometallic aluminium compound and the water is comprised between 1:1 and 100:1. In the embodiment examples, only triisobutylaluminium and triisohexylaluminium are used as the organometallic aluminium compounds.

International Patent Application WO 96/02580 describes improved catalytic systems comprising:

(A) a cyclopentadienyl compound of formula:



in which M is Ti, Zr or Hf; $C_5R^1_{x-m}H_{5-x}$ and $C_5R^1_{y-m}H_{5-y}$ are equally or differently substituted cyclopentadienyl rings; the substituents R^1 , the same or different from each other, are alkyl, alkenyl, aryl, alkylaryl or arylalkyl radicals, which have 1 to 20 carbon atoms, optionally containing Si or Ge atoms or groups $Si(CH_3)_3$, or two or four substituents R^1 of one and the same cyclopentadienyl group can also form one or two rings, having 4 to 6 carbon atoms; R^2 is a bridging group linking the two cyclopentadienyl rings and is selected from CR^3_2 , $C_2R^3_4$, SiR^3_2 , $Si_2R^3_4$, GeR^3_2 , $Ge_2R^3_4$, $R^3_2SiCR^3_2$, NR^1 and PR^1 , wherein the substituents R^3 , the same or different from each other, are R^1 or hydrogen, or two or four substituents R^3 can also form one or two rings, having 3 to 6 carbon atoms; the substituents Q, the same or different from each other, are halogen, hydrogen, R^1 , OR^1 , SR^1 , NR^1_2 or PR^1_2 ; m can be 0 or 1; n can be 0 or 1, being 1, if m = 1; x is an integer comprised between (m+1) and 5; and y is an integer comprised between m and 5;

(B) an organometallic aluminium compound of formula:



wherein in the $(\text{CH}_2\text{-CR}^4\text{R}^5\text{R}^6)$ groups, the same or different from each other, R^4 is an alkyl, alkenyl or arylalkyl group, having from 1 to 10 carbon atoms; R^5 is an alkyl, alkenyl, aryl, arylalkyl or alkylaryl group, having from 3 to 50 carbon atoms which is different from a straight alkyl or alkenyl group and, optionally, R^4 and R^5 fused together can form a ring, having from 4 to 6 carbon atoms; R^6 is hydrogen or an alkyl, alkenyl or arylalkyl group, having from 1 to 10 carbon atoms; the R^7 substituents, the same or different from each other, are alkyl, alkenyl, aryl, arylalkyl or alkylaryl radicals, containing from 1 to 10 carbon atoms, optionally containing Si or Ge atoms; w is 1, 2 or 3; z is 0 or 1; $y=3-w-z$; and


(C) water.

The molar ratio between the organometallic aluminium compound and water is comprised between 1:1 and 100:1. The only organometallic aluminium compounds disclosed are those wherein the $(\text{CH}_2\text{-CR}^4\text{R}^5\text{R}^6)$ groups are 2,4,4-trimethyl-pentyl, 2-phenyl-propyl or 1-butene oligomers. According to the cited application, the compound (B) can be contacted with (A) and successively with (C), or can be reacted with (C) and successively with (A); moreover, in the examples, the three components are mixed together at the same time.

It has now surprisingly been found that, by contacting components (A), (B) and (C) described in the above-mentioned European patent application EP 575,875 according to a novel procedure, catalysts can be obtained with higher activity than those obtained according to the prior art.

It is therefore an object of the present invention a catalyst for the polymerisation of olefins, comprising the product obtainable by contacting the following components:

(A) a cyclopentadienyl compound of formula (I):



wherein M is a metal selected from the group consisting of Ti, Zr and Hf; $C_5R^1_{x-m}H_{5-x}$ and $C_5R^1_{y-m}H_{5-y}$ are equally or differently substituted cyclopentadienyl rings; the substituents R^1 , the same or different from each other, are selected from the group consisting of a linear or branched, saturated or unsaturated C_1 - C_{20} alkyl, C_6 - C_{20} aryl, C_7 - C_{20} alkylaryl or C_7 - C_{20} arylalkyl groups radicals, optionally containing one or more atoms belonging to groups 13-16 of the Periodic Table of the Elements (new IUPAC notation), such as B, P, Al, Si, Ge, O and S atoms, or two or four substituents R^1 of the same cyclopentadienyl group form one or two rings, having 4 to 6 carbon atoms; R^2 is a bridging group between the two cyclopentadienyl rings and is selected from the group consisting of CR^3_2 , $C_2R^3_4$, SiR^3_2 , $Si_2R^3_4$, GeR^3_2 , $Ge_2R^3_4$, $R^3_2SiCR^3_2$, NR^1 and PR^1 , wherein the substituents R^3 , the same or different from each other, are hydrogen or have the same meaning of R^1 , or two or four substituents R^3 form one or two rings, having 3 to 6 carbon atoms; the substituents Q, the same or different from each other, are selected from the group consisting of hydrogen, halogen, OH, SH, R^1 , OR^1 , SR^1 , NR^1_2 and PR^1_2 ; m is 0 or 1; n is 0 or 1, being 1 when m=1; x ranges from (m+1) to 5, and preferably between (m+2) and 5; and y ranges from m to 5;

(B) one or more organometallic aluminium compounds of formula (II):



wherein the substituents R^4 , the same or different from each other, are linear or branched, saturated or unsaturated C_1 - C_{20} alkyl or C_7 - C_{20} alkylaryl radicals,

optionally containing Si or Ge atoms, at least one of the substituents R^4 being different from a straight alkyl group; z is 0 or 1; and

(C) water;

the molar ratio between said organometallic aluminium compound (B) and water (C) is comprised between 1:1 and 100:1, preferably between 1:1 and 50:1, and more preferably is 2:1; said catalyst being obtainable by a process comprising the following steps:


- (i) contacting component (A) with part of component (B), in the absence of component (C);
- (ii) contacting part of component (B) with component (C), in the absence of component (A); and successively
- (iii) contacting the products obtained in steps (i) and (ii);


wherein the components (B) used in steps (i) and (ii) can be the same or different from each other.

In the cyclopentadienyl compounds of formula (I), M is preferably zirconium.

When $m=0$ in formula (I), $C_5R^1_{x-m}H_{5-x}$ and $C_5R^1_{y-m}H_{5-y}$ are preferably pentamethyl-cyclopentadienyl, indenyl or 4,5,6,7-tetrahydroindenyl groups; the Q substituents are preferably chlorine atoms or C_1 - C_7 hydrocarbon groups, and more preferably are methyl groups.

Non-limiting examples of cyclopentadienyl compounds of formula (I), wherein $m=0$, are:






wherein Me = methyl, Et = ethyl, Cp = cyclopentadienyl, Ind = indenyl,

H₄Ind = 4,5,6,7-tetrahydroindenyl and Benz = benzyl.

When m=1 in formula (I), C₅R¹_{x-m}H_{5-x} and C₅R¹_{y-m}H_{5-y} are preferably tetramethyl-cyclopentadienyl, indenyl, 4,5,6,7-tetrahydroindenyl, 2-methyl-4,5,6,7-tetrahydroindenyl, 4,7-dimethyl-4,5,6,7-tetrahydroindenyl, 2,4,7-trimethyl-4,5,6,7-tetrahydroindenyl or fluorenyl groups; R² is preferably (CH₃)₂Si< or -CH₂CH₂-; the Q substituents are preferably chlorine atoms or C₁-C₇ hydrocarbon groups, and more preferably methyl groups.

Non-limiting examples of cyclopentadienyl compounds of formula (I), wherein m=1, are:



$\text{Me}_2\text{Si}(2\text{-MeInd})_2\text{MCl}_2$	$\text{Me}_2\text{Si}(4,7\text{-Me}_2\text{Ind})_2\text{MCl}_2$
$\text{Me}_2\text{Si}(5,6\text{-Me}_2\text{Ind})_2\text{MCl}_2$	$\text{Me}_2\text{Si}(2,4,7\text{-Me}_3\text{Ind})_2\text{MCl}_2$
$\text{Me}_2\text{Si}(2\text{-MeH}_4\text{Ind})_2\text{MCl}_2$	$\text{Me}_2\text{Si}(4,7\text{-Me}_2\text{H}_4\text{Ind})_2\text{MCl}_2$
$\text{Me}_2\text{Si}(2,4,7\text{-Me}_3\text{H}_4\text{Ind})_2\text{MCl}_2$	$\text{Me}_2\text{Si}(\text{Benz}[\text{e}]\text{Ind})_2\text{MCl}_2$
$\text{Me}_2\text{Si}(2\text{-Me-Benz}[\text{e}]\text{Ind})_2\text{MCl}_2$	$\text{Me}_2\text{Si}(2\text{-Me-4-Ph-Ind})_2\text{MCl}_2$
$\text{Me}_2\text{Si}(2\text{-Me-4-naphtyl-Ind})_2\text{MCl}_2$	$\text{Me}_2\text{C}(2\text{-MeInd})_2\text{MCl}_2$
$\text{Me}_2\text{C}(2\text{-Me-4-Ph-Ind})_2\text{MCl}_2$	$\text{Me}_2\text{C}(3\text{-tButInd})_2\text{MCl}_2$
$\text{H}_2\text{C}(3\text{-tButInd})_2\text{MCl}_2$	$\text{Me}_2\text{C}(3\text{-iPrInd})_2\text{MCl}_2$
$\text{H}_2\text{C}(3\text{-iPrInd})_2\text{MCl}_2$	$\text{Me}_2\text{Si}(3\text{-tButInd})_2\text{MCl}_2$

wherein Me = methyl, Cp = cyclopentadienyl, Ind = indenyl, Flu = fluorenyl, Ph = phenyl and H_4Ind = 4,5,6,7-tetrahydroindenyl.


In component (B) of the catalyst of the invention, according to a preferred embodiment, said organometallic aluminium compounds have formula (III):



wherein in the $(\text{CH}_2\text{-CR}^4\text{R}^5\text{R}^6)$ groups, the same or different from each other, R^4 is a linear or branched, saturated or unsaturated $\text{C}_1\text{-C}_{10}$ alkyl or $\text{C}_7\text{-C}_{10}$ arylalkyl group; R^5 is a saturated or unsaturated $\text{C}_3\text{-C}_{50}$ alkyl, $\text{C}_6\text{-C}_{50}$ aryl, $\text{C}_7\text{-C}_{50}$ arylalkyl or alkylaryl group, which is different from a straight alkyl or alkenyl group; or R^4 and R^5 form a ring, having from 4 to 6 carbon atoms; R^6 is hydrogen or a linear or branched, saturated or unsaturated $\text{C}_1\text{-C}_{10}$ alkyl, $\text{C}_7\text{-C}_{10}$ arylalkyl group; the R^7 substituents, the same or different from each other, are linear or branched, saturated or unsaturated $\text{C}_1\text{-C}_{10}$ alkyl, $\text{C}_6\text{-C}_{10}$ aryl, $\text{C}_7\text{-C}_{10}$ arylalkyl or alkylaryl groups, optionally containing Si or Ge atoms; w is 1, 2 or 3; z is 0 or 1; and $y=3-w-z$.

A particularly preferred compound corresponding to formula (III) is tris(2,4,4-trimethylpentyl)aluminium (TIOA).

According to another preferred embodiment of the catalyst of the invention, said organometallic aluminium compounds, to be used as component (B), correspond to formula (IV):



wherein R^4 is a linear or branched, saturated or unsaturated $\text{C}_1\text{-C}_{10}$ alkyl or $\text{C}_7\text{-C}_{10}$ arylalkyl group; R^5 is hydrogen or a linear or branched, saturated or unsaturated $\text{C}_1\text{-C}_{10}$ alkyl or $\text{C}_7\text{-C}_{10}$ arylalkyl group; R^6 and R^7 , the same or different from each other, are linear or branched, saturated or unsaturated $\text{C}_1\text{-C}_{10}$ alkyl, $\text{C}_6\text{-C}_{10}$ aryl, $\text{C}_7\text{-C}_{10}$ arylalkyl or alkylaryl groups; R^8 is hydrogen or a linear or branched, saturated or unsaturated $\text{C}_1\text{-C}_{10}$ alkyl, $\text{C}_6\text{-C}_{10}$ aryl, $\text{C}_7\text{-C}_{10}$ arylalkyl or alkylaryl group; R^9 is a linear or branched, saturated or unsaturated $\text{C}_1\text{-C}_{10}$ alkyl or $\text{C}_7\text{-C}_{10}$ arylalkyl group; a carbon atom in the compound of formula (IV) being optionally replaced by a Si or Ge atom; w is 1, 2 or 3; z is 0 or 1; and $q=3-w-z$.

Particularly preferred compounds corresponding to formula (IV) are tris(2,3,3-trimethylbutyl)aluminium (TTMBA) and tris(2,3-dimethylbutyl)aluminium (TDMBA).

The molar ratio between said organometallic aluminium compound (component B) and said cyclopentadienyl compound (component C) is preferably comprised between 50 and 50,000, and more preferably between 500 and 5,000.

According to the invention, both in step (i) and (ii), component (B) can suitably comprise a mixture of two or more organometallic aluminum compounds of formula (II), and preferably of compounds of formula (III) and/or (IV).

Moreover, both in steps (i) and (ii), component (B) can be used in combination with organometallic aluminum compounds other than those of formulae (II), (III) and (IV), or in mixture with other compatible cocatalysts known in the state of the art.

In the organometallic aluminium compounds of formulae (II), (III) or (IV), z is 0 or 1. As it is known in the state of the art, aluminium trialkyls may contain small amounts of dialkylaluminium hydride; the hydride content can slightly change during prolonged storage periods and depending on the storage temperature. Therefore, according to a preferred embodiment of the invention, component (B) is a mixture of the two organometallic aluminium compounds of formula (II), (III) and/or (IV) wherein $z=0$ and $z=1$, so that the molar ratio between the hydrogen atoms directly bound to aluminium and aluminium atoms (i.e. the overall z value) is lower than 0.8, and even more preferably ranges from 0.02 to 0.3. Mixtures of organometallic aluminium compounds having said overall z values can be prepared with methods known in the state of the art, for instance by mixing the corresponding trialkylaluminium and dialkylaluminium hydride in appropriate molar ratios.

Another object of the present invention is a process for the preparation of a catalyst as described above, said process comprising the following steps:

- (i) contacting component (A) with part of component (B) in the absence of component (C);
- (ii) contacting part of component (B) with component (C) in the absence of component (A); and successively
- (iii) contacting the products obtained in steps (i) and (ii);

wherein the components (B) used in steps (i) and (ii) can be the same or different from each other.

In step (i), component (A) is preferably contacted with component (B) in a suitable solvent, such as toluene; the concentration of component (A) in said solution is preferably comprised between 10^{-2} and 10^{-8} mol/l. The amount of component (B) used in step (i) preferably ranges from 1 to 80 %mol of the total amount of (B) used in the process of the invention, and more preferably from 2 to 10 %mol. The precontact can be carried out in the presence of small amounts of monomer. The contact time is generally comprised between 1 and 60 minutes, preferably between 5 and 20 minutes.

In step (ii) of the process of the invention, according to a particular embodiment of the invention, water can be gradually added to component (B) in solution, in an aliphatic or aromatic inert hydrocarbon solvent, such as heptane or toluene. In said solution, the concentration of the product obtainable by contacting said organometallic aluminium compound and water is preferably comprised between 10^{-2} and 10^{-3} mol/l. The amount of component (B) used in step (ii) preferably ranges from 20 to 99 %mol of the total amount of (B) used in the process of the invention, and more preferably from 90 to 98 %mol.

According to another embodiment, the water can be introduced in the monomer or in one of the monomers to be polymerised, and contacted with said organometallic aluminium compound.

According to still another embodiment, the water can be reacted in a combined form, as a hydrated salt, or it can be adsorbed or absorbed on an inert support such as silica.

The contact time is generally comprised between 1 and 60 minutes, preferably between 5 and 20 minutes.

The catalysts of the present invention can be used on inert supports, such as silica, alumina, styrene/divinylbenzene copolymers, homopolymers and copolymers of ethylene and α -olefins; the thus obtained solid systems can be suitably used in gas phase polymerizations.

The catalysts of the present invention can be used in the polymerisation reactions of olefins. Therefore, according to further object, the invention provides a process for the polymerisation of an olefin carried out in the presence of a catalyst as described above.

Olefins which can be polymerised with the process of the present invention are, for instance, α -olefins of formula $\text{CH}_2=\text{CHR}$, wherein R is hydrogen or a $\text{C}_1\text{-C}_{20}$ alkyl radical.

The catalysts according to the present invention can conveniently be used in ethylene homopolymerization, in particular for the preparation of HDPE, and in ethylene copolymerization, in particular for the preparation of LLDPE. In ethylene polymerisation, according to a preferred embodiment of the invention, component (B) is a mixture of the two organometallic aluminium compounds of formula (II) wherein $z=0$ and $z=1$, in such amounts that the molar ratio between the hydrogen atoms directly bound to aluminium and aluminium atoms (i.e. the overall z value) preferably ranges from 0.02 to 0.3. More specifically, in step (i), said overall z value is preferably higher than 0.02, and more preferably is about 0.09; in step (ii), said overall z value is preferably lower than 0.2.

The process according to the present invention allow to prepare LLDPE copolymers having a content of ethylene units of between 80 and 99 mol%; said copolymers have a density comprised between 0.87 and 0.95 g/cm^3 and are characterised by a uniform distribution of the α -olefin units along the polymeric chain.

Comonomers which can be suitably used in ethylene copolymers comprise α -olefins of formula $\text{CH}_2=\text{CHR}$, wherein R is a linear, branched or cyclic $\text{C}_1\text{-C}_{20}$ alkyl, and cycloolefins. Examples of such olefins are propylene, 1-butene, 1-pentene, 4-methyl-1-pentene, 1-hexene, 1-octene, allylcyclohexane, cyclopentene, cyclohexene, norbornene and 4,6-dimethyl-

1-heptene. The units deriving from the olefins of formula $\text{CH}_2=\text{CHR}$ or from cycloolefins are generally present in the copolymers in a quantity ranging from 1 to 20 mol%.

The copolymers can also contain units deriving from polyenes, in particular from conjugated or non-conjugated, linear or cyclic dienes, such as 1,4-hexadiene, isoprene, 1,3-butadiene, 1,5-hexadiene and 1,6-heptadiene.

According to another object of the invention, the above catalysts can be used in propylene homopolymerization, in particular for the production of isotactic polypropylene.

In propylene polymerisation, according to a preferred embodiment of the invention, component (B) is a mixture of the two organometallic aluminium compounds of formula (II) wherein $z=0$ and $z=1$, in such amounts that the molar ratio between the hydrogen atoms directly bound to aluminium and aluminium atoms (i.e. the overall z value) preferably ranges from 0.02 to 0.3. More specifically, in step (i), said overall z value is preferably higher than 0.02, and more preferably is about 0.09; in step (ii), said overall z value is preferably lower than 0.4.

According to a further embodiment, the catalysts of the invention can be advantageously used in the preparation of elastomeric copolymers of ethylene with α -olefins of formula $\text{CH}_2=\text{CHR}$, wherein R is a $\text{C}_1\text{-C}_{10}$ alkyl radical, optionally containing minor proportions of polyenes units.

The saturated elastomeric copolymers obtainable with the catalysts of the present invention contain from 15 to 85 mol% of ethylene units, the complement to 100% consisting of units of one or more α -olefins and/or of a non-conjugated diolefin able to cyclopolymerize. The unsaturated elastomeric copolymers also contain, in addition to the units deriving from the polymerisation of ethylene and α -olefins, minor proportions of unsaturated units deriving from the copolymerization of one or more polyenes. The content of unsaturated units can vary from 0.1 to 5% by moles and it is preferably comprised between 0.2 and 2% by moles.

The elastomeric copolymers obtainable with the catalysts of the invention are endowed with valuable properties, such as a low content of ashes and uniformity of distribution of the comonomers along the copolymeric chain.

The α -olefins which can be used as comonomers in the elastomeric copolymers comprise propylene, 1-butene, 4-methyl-1-pentene, 1-hexene and 1-octene.

Polyenes which can be used in elastomeric copolymers comprise:

polyenes able to give unsaturated units, such as:

- linear, non-conjugated dienes such as 1,4-hexadiene trans, 1,4-hexadiene cis, 6-methyl-1,5-heptadiene, 3,7-dimethyl-1,6-octadiene, 11-methyl-1,10-dodecadiene;
- monocyclic diolefins such as, for example, cis-1,5-cyclooctadiene and 5-methyl-1,5-cyclooctadiene;
- bicyclic diolefins such as for example 4,5,8,9-tetrahydroindene and 6 and/or 7-methyl-4,5,8,9-tetrahydroindene;
- alkenyl or alkyliden norbornenes such as for example, 5-ethyliden-2-norbornene, 5-isopropyliden-2-norbornene, exo-5-isopropenyl-2-norbornene, 5-vinyl-2-norbornene;
- polycyclic diolefins such as, for example, dicyclopentadiene, tricyclo-[6.2.1.0^{2,7}]4,9-undecadiene and the 4-methyl derivative thereof;

non-conjugated diolefins able to cyclopolymerize, such as 1,5-hexadiene, 1,6-heptadiene, 2-methyl-1,5-hexadiene; conjugated dienes, such as butadiene, 1,3-pentadiene and isoprene.

A further interesting use of the catalysts according to the present invention is in the preparation of cycloolefin polymers. Monocyclic and polycyclic olefin monomers can be either

homopolymerized or copolymerized, also with linear olefin monomers. Non limitative examples of cycloolefin polymers which can be prepared with the catalysts of the present invention are described in the European patent applications EP-501,370 and EP-407,870.

The polymerisation processes of the present invention can be carried out in liquid phase, optionally in the presence of inert hydrocarbon solvents, or in gas phase. Said hydrocarbon solvent can be either aromatic (such as toluene) or aliphatic (such as propane, hexane, heptane, isobutane, cyclohexane and 2,2,4-trimethylpentane).

The polymerisation temperature generally ranges from about 0°C to about 250°C. In particular, in the processes for the preparation of HDPE and LLDPE, it is preferably comprised between 20°C and 150°C and, more preferably between 40°C and 90°C, whereas for the preparation of elastomeric copolymers it is preferably comprised between 0°C and 200°C and, more preferably between 20°C and 100°C.

The molecular weight of polymers can be varied simply by varying the polymerisation temperature, the type or the concentration of the catalyst components, or by using molecular weight regulators, such as hydrogen.

The molecular weight distribution can be varied by using mixtures of different cyclopentadienyl compounds or by carrying out the polymerisation in several stages which differ in the polymerisation temperature and/or the concentrations of molecular weight regulator.

The polymerisation yield depends on the purity of the metallocene components in the catalyst. Therefore the metallocene obtained by the process of the invention may be used as such, or subjected to purification treatments.

The following examples are given for illustrative purposes and do not restrict the invention.

EXAMPLES

SYNTHESIS OF THE CATALYTIC COMPONENTS

CYCLOPENTADIENYL COMPOUNDS

rac-Et(1-H₄Ind)₂ZrCl₂ (*r*-EBTHIZrCl₂)

The product available from Witco was used.

rac-Et(1-Ind)₂ZrCl₂ (*r*-EBIZrCl₂)

This was prepared according to the procedure described in EP 575,875.

Organoaluminium compounds

General Procedures

All reactions were carried out under nitrogen in the glove box or under Schlenk conditions using oven-dried glassware. The toluene solvent was dried by refluxing over Na/benzophenone and the xylene solvent (Aldrich anhydrous grade) was dried over 4Å molecular sieves. All alkenes were dried over 4Å molecular sieves prior to use.

tris(2,3,3-trimethyl-butyl)aluminium (TTMBA)

In the glove box, CH₂=C(Me)(CMe₃) (81.5 g, 0.831 mol; "99%" ex-Wiley) was dissolved in dry *p*-xylene (ca. 145 ml) in a 500 ml 3-neck flask. Al{CH₂CHMe₂}₃ (TIBA, 35.0 ml, 0.139 mol, ex-Witco) was added over 10 min by syringe to the rapidly stirred solution at ambient temperature. The stoppered reaction flask was removed from the glove box and a reflux condenser and nitrogen line attached in the fume hood. The isobutene product was collected using a graduated collection vessel immersed in a -78°C acetone/dry ice bath. The reaction mixture was warmed over 35 minutes to an internal temperature of 105.6°C. The reaction was allowed to reflux for 20 h (final reflux temperature 121.2 °C), affording ca. 95% of the theoretical maximum yield of isobutene (ca. 2.9 equivalents/Al). Despite the low boiling point of CH₂=C(Me)(CMe₃), only a negligible amount of this olefin was collected in the cold

trap. The remaining olefin and solvent were removed *in vacuo* (80 °C, 0.05 mbar, 90 min) utilising a dry ice/acetone bath to give 43.0 g (95.5% yield based on TIBA) of tris(2,3,3-trimethyl-butyl)aluminium (TTMBA). The colourless oil was shown by NMR spectroscopy to be a clean single species, showing no sign of AlH or AlOR resonances.

tris(2,3-dimethyl-butyl)aluminium (TDMBA)

TDMBA was prepared analogously to TTMBA from the reaction of $\text{CH}_2=\text{CHMeCHMe}_2$ (42.6 g, 0.507 mol, 99% ex-Wiley) with TIBA (21.4 ml, 0.085 mol, ex-Witco) in dry xylene (90 ml; isomer mixture) in a 500 ml 3-neck flask. The mixture was allowed to reflux for 20 h (range reflux temperature: 85 - 109 °C), affording 30 ml of volatile material in the dry ice trap consisting of ca. 8 ml of $\text{CH}_2=\text{CHMeCHMe}_2$ and ca. 22 ml of isobutene (ca. 100% of theoretical). The remaining olefin and solvent were removed *in vacuo* (60 °C, 0.7 mbar, 90 min) utilizing a dry ice/acetone trap to give 23.4 g (97% yield based on TIBA) of tris(2,3-dimethyl-butyl)aluminium (TDMBA). The colorless oil was shown by ^1H and ^{13}C NMR spectroscopy to be clean TDMBA contaminated by 4 % (molar basis)* of $\text{Al}(\text{CH}_2\text{CHMe}_2)(\text{CH}_2\text{CHMeCH}_2\text{Me}_2)_2$; no NMR resonances due to AlH or AlOR fragments were observed.

tris(2,4,4-trimethyl-pentyl)aluminium (TIOA)

This was prepared according to the method described in Liebigs Ann. Chem., Volume 629, Ziegler et al. "Aluminiumtrialkyle und Dialkyl-aluminiumhydride aus Aluminiumisobutyl-Verbindungen [Aluminium trialkyls and dialkyl-aluminium hydrides from aluminium isobutyl compounds]", pages 14-19.

tris(2-methyl-propyl)aluminium (TIBA)

The product available from Witco was used.

Triisooctylaluminumoxane (TIOAO)

3.45 ml of a TIOA solution (1 M in hexane) were added at room temperature to 5 ml of toluene, previously deoxygenated and distilled over triisobutylaluminum. 0.031 ml of H₂O were then added at room temperature with a syringe and the resulting solution was stirred for 10 minutes at room temperature.

Example 1**Ethylene/propylene copolymerization**

The ethylene/propylene copolymerization was performed in a 4.26 l steel autoclave equipped with mechanical stirrer, external jacket for thermostating the polymerisation bath, valves for the introduction of liquids and gases. A mixture of vapour/water was allowed to flow inside the external jacket and their relative amount was controlled to set the polymerisation temperature. 1317 grams of hexane, 1.688 mmol of TIOAO, 0.1879 mmol of TIOA, 396.8 grams of propylene, 37.4 grams of ethylene, 15 ml of hydrogen were charged into the autoclave. The internal temperature of the autoclave was brought to 50°C and it was waited until a constant pressure, 8.8 barg, was achieved. In this way, the thermodynamic equilibrium in the polymerisation bath was considered to be achieved. At this time, in a 25 ml schlenk, 0.8 mg of racemic ethylene bis-tetrahydroindenyl zirconium dichloride was dissolved in 5 ml of a TIOA solution in hexane, containing 0.188 mmol of TIOA. The solution was allowed to stir for 10 minutes and was then injected into the autoclave by using a slight overpressure (0.5 bar) of ethylene.

During the polymerisation test, ethylene was fed to keep constant the polymerisation pressure. The polymerisation was quenched after 17 minutes, when 40 g of ethylene had been fed, by injecting CO.

The polymer was recovered by precipitation in acetone and filtration and was dried under reduced pressure at 60°C for 3 hours. 86 grams was obtained. The ethylene content was 60.6% by weight and the intrinsic viscosity 3.34 dl/g.

Example 2 (Comparative)

Ethylene/propylene copolymerization

The polymerisation test was performed as in example 1, except that:

- (i) 16.9 mg of H₂O were fed to the autoclave before the monomers.
- (ii) No aluminium compounds, either TIOA or TIOAO, were charged into the autoclave.
- (iii) 0.8 mg of rac-EBTHIZrCl₂ were dissolved in 5 ml of a TIOA solution in hexane, containing 1.88 mmol of TIOA.
- (iv) The polymerisation was stopped when 40 g of ethylene had been fed, in this case after 23 minutes.
- (v) 80 grams of polymer were recovered.

The ethylene content was 59% by weight and the intrinsic viscosity 3.16 dl/g.

Example 3

Ethylene/propylene copolymerization

The ethylene/propylene copolymerization was performed in a 250 ml glass flask equipped with a magnetic stirrer, a thermocouple, valves for the introduction of liquids and gases and a tube to bubble the mixture of gaseous monomers into the polymerisation solution:

100 ml of toluene containing 3.45 mmol of TIOAO were fed into the glass autoclave and an ethylene/propylene mixture, with 60% by weight of ethylene, was allowed to bubble into the solution and to flow through it at a flow rate of 1.5 l/min. The temperature of the toluene

solution was brought to 50°C by using an oil bath. The total pressure, under these conditions, was 80 mmHg.

At this time, in a 10 ml schlenk, 1.47 mg of rac-EBTHIZrCl₂ were dissolved in 5 ml of toluene containing 34.5 µmol of TIOA. The solution was allowed to stir for 1 minute and was then injected into the glass autoclave. The polymerisation was stopped after 15 minutes by injecting 2 ml of methanol. The polymer was precipitated with a large amount of methanol, filtered and dried under reduced pressure at 50°C for 8 hours. 3.9 grams of polymer were weighed. The ethylene content was 65% by weight.

Example 4 (Comparative)

Ethylene/propylene copolymerization

The copolymerization was performed as in example 3 except that the metallocene was dissolved in toluene in the absence of any aluminium compound. 3.2 grams of polymer were obtained.

Examples 5-10

Polymerisation of Propylene

A 5 litre reactor equipped with helical stirrer, steam/water temperature control and a catalyst injection system was heated to 150-160°C overnight, whilst purging with nitrogen, cooled and then pickled at 70°C using a mixture of TIBA (0.25 g), toluene (20 ml) and propylene (500 g). The pickle mixture was removed and the reactor then charged with 1650 g liquid propylene, whilst increasing the temperature from 20°C to 50°C.

Separately, 9.00 mmol of TIOA was dissolved in 20 g of toluene in a bottle with a septum cap. The solution was cooled to 0-4°C using an ice bath, and 81 µl of water (4.5 mmol) added in four shots using a 25 µl syringe, whilst maintaining the temperature below 15°C

and purging the solution with nitrogen. The resulting solution was introduced into the reactor using an injection system, washed in using 20 ml of toluene.

Meanwhile, 9.7 mg of *rac*-Et(1-Ind)₂ZrCl₂ (*r*-EBIZrCl₂; 23.2 μmol) was dissolved in 17.6 g of toluene, and an amount of the solution obtained containing 3.0 μmol of metallocene was reacted with the indicated amount of the compound indicated in table 2 as "prealkylating agent", resulting in a colour change from yellow to light yellow. Ten minutes after the introduction of the hydrolysed alkylaluminium mixture into the reactor, the alkylated zirconocene solution (aged for 5 minutes) was injected into the reactor (using 20 ml toluene). The polymerisation was continued for 1 hour at a constant temperature of 50 °C using 840-1100 rpm stirring. The polymerisation was then stopped by injection of 5-10 ml methanol. The heating was then discontinued and the propylene rapidly vented and the powder polypropylene collected. Fouled material was removed using hot toluene and precipitated with methanol. The polypropylene fractions were dried (70-80 °C, 200 mbar, nitrogen purge) and combined to give the total yield of polypropylene.

The data relating to the activity of the catalytic system are indicated in Table 2.

Example 11 (Comparative)

Polymerisation of Propylene

The pickle procedure described in Examples 5 to 10 was followed and the reactor then allowed to cool to 25°C. 81 μl of water (4.5 mmol) was then introduced into the autoclave (utilising a septum attachment connected to the propylene feed tube) using a syringe. The reactor was then charged with 1650 g of propylene, rapidly heated to 50°C, and the system then allowed to reach equilibrium over 60 min.

Separately 3.28 g of TIOA (9.0 mmol) was added to a solution of *r*-EBIZrCl₂ (3.0 μmol) in toluene (6.0 g) and the solution stirred for 20 min at 25°C. The alkylated zirconocene solution was then injected into the reactor (using 20 ml toluene). The polymerisation and polymer work-up were performed as described in Examples 5 to 10. The polymerisation conditions and the data relating to the obtained polymer are indicated in Table 2.

Example 12 (Comparative)

Polymerisation of Propylene

The general procedure described in Examples 5 to 10 was followed except that metallocene prealkylation was not performed: the solution of the metallocene in (alkylaluminium-free) toluene (1.31 g) was directly injected into the reactor (using an additional 20 ml of toluene). The amounts of metallocene, aluminium compound and water utilised, and the polymerisation conditions, as well as the data relating to the obtained polymer are indicated in Table 2.

Example 13

Polymerization of Propylene

The general procedure described in Examples 5-10 was followed but using Al{CH₂CHMeCHMe₂}₃ (TDMBA) as organometallic aluminium compound according to the present invention, instead of TIOA and operating with the amounts of metallocene, aluminium compound and water indicated in Table 2. The polymerization conditions and the data relating to the obtained polymer are indicated in Table 2.

Example 14 (Comparative)

Polymerisation of Propylene

The procedure of Example 13 was followed, with the exception that the metallocene prealkylation was not performed: the solution of the metallocene in (alkylaluminium-free) toluene was directly injected into the reactor. The amounts of metallocene, aluminium compound and water utilised, and the polymerisation conditions, as well as the data relating to the obtained polymer are indicated in Table 2.

Example 15

Polymerization of Propylene

The general procedure described in Examples 5-10 was followed but using $\text{Al}\{\text{CH}_2\text{CH}(\text{Me})\text{CMe}_3\}_3$ (TTMBA) as organometallic aluminium compound according to the present invention, instead of TIOA and operating with the amounts of metallocene, aluminium compound and water indicated in Table 2. The polymerization conditions and the data relating to the obtained polymer are indicated in Table 2.

Example 16 (Comparative)

Polymerisation of Propylene

The procedure of Example 15 was followed, with the exception that the metallocene prealkylation was not performed: the solution of the metallocene in (alkylaluminium-free) toluene was directly injected into the reactor. The amounts of metallocene, aluminium compound and water utilised, and the polymerisation conditions, as well as the data relating to the obtained polymer are indicated in Table 2.

Example 17

Polymerization of Propylene

The general procedure described in Examples 5-10 was followed but using TTMBA as organometallic aluminium compound in the metallocene prealkylation (step (i)) and a

mixture of TIOA/TTMBA, at a molar ratio of 29:1, in step (ii), wherein TTMBA is $\text{Al}\{\text{CH}_2\text{CH}(\text{Me})\text{CMe}_3\}_3$; the amounts of metallocene, aluminium compound and water used in the procedure are indicated in Table 2, as well as the polymerization conditions and the data relating to the obtained polymer.

Table 1: Ethylene/propylene copolymerisation

Example	Metallocene		Prealkylating agent		Reactor		Total Al/Zr	Time	Yield	Activity
	Type	μmol	Type	Mmol	Compound	mmol				
1	<i>r</i> -EBTHIZrCl ₂	1.88	TIOA	0.188	TIOA/ TIOAO	0.1879/ 1.688	1100	17	86	830
2 (comp)	<i>r</i> -EBTHIZrCl ₂	1.88	TIOA	1.88	H ₂ O	0.94	1000	23	80	610
3	<i>r</i> -EBTHIZrCl ₂	3.45	TIOA	0.0345	TIOAO	3.45	1010	15	3.88	25
4 (comp)	<i>r</i> -EBTHIZrCl ₂	3.45			TIOAO	3.45	1000	15	3.25	21

Table 2: Propylene polymerisation

Example	Metallocene		Prealkylating agent		Cocatalyst			Total Al/Zr	Yield g pol.	Activity kg/gZr.h
	Type	μmol	Type	mmol	Type	mmol	Al/H ₂ O mol			
5	<i>r</i> -EBIZrCl ₂	3.0	TIOA	0.30	TIOA	9.00	2	3100	470	1720
6	<i>r</i> -EBIZrCl ₂	3.0	TTMBA	0.30	TIOA	9.00	2	3100	585	2140
7	<i>r</i> -EBIZrCl ₂	3.0	TIBA	0.30	TIOA	9.00	2	3100	374	1370
8	<i>r</i> -EBIZrCl ₂	3.0	TIOA	0.03	TIOA	9.00	2	3010	253	920
9	<i>r</i> -EBIZrCl ₂	3.0	TIOA	0.15	TIOA	9.00	2	3050	510	1860
10	<i>r</i> -EBIZrCl ₂	3.0	TIOA	1.50	TIOA	9.00	2	3500	421	1540
11 (Comp)*	<i>r</i> -EBIZrCl ₂	3.0	TIOA	9.00	-	-	2	3000	44	160
12 (Comp)	<i>r</i> -EBIZrCl ₂	3.0	-	-	TIOA	9.00	2	3000	113	410
13	<i>r</i> -EBIZrCl ₂	2.0	TDMBA	0.30	TDMBA	9.00	2	4690	525	2880
14 (Comp)	<i>r</i> -EBIZrCl ₂	2.0	-	-	TDMBA	9.00	2	4500	0	0
15**	<i>r</i> -EBIZrMe ₂	3.0	TTMBA	0.34	TTMBA	10.1	2.3	3500	850	3650
16 (Comp)	<i>r</i> -EBIZrMe ₂	3.0	-	-	TTMBA	10.1	2.3	3380	480	1750
17	<i>r</i> -EBIZrCl ₂	3.0	TTMBA	0.35	TIOA/ TTMBA	9.10	2	3130	640	2340


*Mixture of TIOA/ *r*-EBIZrCl₂ added to water in autoclave.

** Polymerization time of 51 minutes.

CLAIMS

1. A catalyst for the polymerisation of olefins comprising the product obtainable by contacting the following components:

(A) a cyclopentadienyl compound of formula (I):



wherein M is a metal selected from the group consisting of Ti, Zr and Hf; $C_5R^1_{x-m}H_{5-x}$ and $C_5R^1_{y-m}H_{5-y}$ are equally or differently substituted cyclopentadienyl rings; the substituents R^1 , the same or different from each other, are selected from the group consisting of linear or branched, saturated or unsaturated C_1 - C_{20} alkyl, C_6 - C_{20} aryl, C_7 - C_{20} alkylaryl or C_7 - C_{20} arylalkyl radicals, optionally containing one or more atoms belonging to groups 13-16 of the Periodic Table of the Elements (new IUPAC notation), or two or four substituents R^1 of the same cyclopentadienyl group form one or two rings, having 4 to 6 carbon atoms; R^2 is a bridging group between the two cyclopentadienyl rings and is selected from the group consisting of CR^3_2 , $C_2R^3_4$, SiR^3_2 , $Si_2R^3_4$, GeR^3_2 , $Ge_2R^3_4$, $R^3_2SiCR^3_2$, NR^1 and PR^1 , wherein the substituents R^3 , the same or different from each other, are hydrogen or have the same meaning of R^1 , or two or four substituents R^3 form one or two rings, having 3 to 6 carbon atoms; the substituents Q, the same or different from each other, are selected from the group consisting of hydrogen, halogen, OH, SH, R^1 , OR^1 , SR^1 , NR^1_2 and PR^1_2 ; m is 0 or 1; n is 0 or 1, being 1 when m=1; x ranges from (m+1) to 5; y ranges from m to 5;

(B) one or more organometallic aluminium compounds of formula (II):



wherein the substituents R^4 , the same or different from each other, are linear or branched, saturated or unsaturated C_1 - C_{20} alkyl or C_7 - C_{20} alkylaryl radicals, optionally containing Si or Ge atoms, at least one of the substituents R^4 being different from a straight alkyl group; z is 0 or 1; and

(C) water;


the molar ratio between said organometallic aluminium compound said water being comprised between 1:1 and 100:1;

said catalyst being obtainable by a process comprising the following steps:

- (i) contacting component (A) with part of component (B) in the absence of component (C);
- (ii) contacting part of component (B) with component (C) in the absence of component (A); and successively
- (iii) contacting the products obtained in steps (i) and (ii);

wherein said components (B) used in steps (i) and (ii) can be the same or different from each other.


2. The catalyst according to claim 1, wherein said component (B) corresponds to formula (III):



Wherein, in the $(CH_2-CR^4R^5R^6)$ groups, the same or different from each other, R^4 is a linear or branched, saturated or unsaturated C_1 - C_{10} alkyl or C_7 - C_{10} arylalkyl group; R^5 is a saturated or unsaturated C_3 - C_{50} alkyl, C_6 - C_{50} aryl, C_7 - C_{50} arylalkyl or alkylaryl group, which is different from a straight alkyl or alkenyl group; or R^4 and R^5 form a ring, having from 4 to 6 carbon atoms; R^6 is hydrogen or a linear or branched, saturated or

unsaturated C₁-C₁₀ alkyl or C₇-C₁₀ arylalkyl group; the R⁷ substituents, the same or different from each other, are linear or branched, saturated or unsaturated C₁-C₁₀ alkyl, C₆-C₁₀ aryl, C₇-C₁₀ arylalkyl or alkylaryl groups, optionally containing Si or Ge atoms; w is 1, 2 or 3; z is 0 or 1; and y=3-w-z.

3. The catalyst according to claim 2, wherein said component (B) is tris(2,4,4-trimethyl-pentyl)aluminium.
4. The catalyst according to claim 1, wherein said component (B) corresponds to formula (IV):



wherein R⁴ is a linear or branched, saturated or unsaturated C₁-C₁₀ alkyl or C₇-C₁₀ arylalkyl group; R⁵ is hydrogen or a linear or branched, saturated or unsaturated C₁-C₁₀ alkyl or C₇-C₁₀ arylalkyl group; R⁶ and R⁷, the same or different from each other, are linear or branched, saturated or unsaturated C₁-C₁₀ alkyl, C₆-C₁₀ aryl, C₇-C₁₀ arylalkyl or alkylaryl groups; R⁸ is hydrogen or a linear or branched, saturated or unsaturated C₁-C₁₀ alkyl, C₆-C₁₀ aryl, C₇-C₁₀ arylalkyl or alkylaryl group; R⁹ is a linear or branched, saturated or unsaturated C₁-C₁₀ alkyl or C₇-C₁₀ arylalkyl group; a carbon atom in the compound of formula (II) being optionally replaced by a Si or Ge atom; w is 1, 2 or 3; z is 0 or 1; and q=3-w-z.

5. The catalyst according to claim 4, wherein said component (B) is tris(2,3,3-trimethyl-butyl)aluminium or tris(2,3-dimethyl-butyl)aluminium.
6. The catalyst according to any of claims 1 to 5, wherein said component (B) is a mixture of the two organometallic aluminium compounds of formula (II), wherein z=0 and z=1,

so that the molar ratio between the hydrogen atoms directly bound to aluminium and aluminium atoms is lower than 0.8.

7. The catalyst according to claim 6, wherein said molar ratio between the hydrogen atoms directly bound to aluminium and aluminium atoms ranges from 0.02 to 0.3.
8. The catalyst according to any of claims 1 to 7, wherein the molar ratio between said organometallic aluminium compound and said water is 2.
9. The catalyst according to any of claims 1 to 8, wherein the molar ratio between the aluminium of component (B) and the metal M of component (A) is comprised between 50 and 50,000.
10. The catalyst according to any of claims 1 to 9 wherein, in said cyclopentadienyl compound of formula (I), M is zirconium.
11. The catalyst according to any of claims 1 to 10 wherein, in said cyclopentadienyl compound of formula (I), m is=0, and $C_5R^1_{x-m}H_{5-x}$ and $C_5R^1_{y-m}H_{5-y}$ are selected from the group consisting of tetramethyl-cyclopentadienyl, pentamethyl-cyclopentadienyl, indenyl and 4,5,6,7-tetrahydroindenyl.
12. The catalyst according any of claims 1 to 10 wherein, in said cyclopentadienyl compound of formula (I), m is=1; $C_5R^1_{x-m}H_{5-x}$ and $C_5R^1_{y-m}H_{5-y}$ are selected from the group consisting of tetramethyl-cyclopentadienyl, indenyl, 2-methyl-indenyl, 4,7-dimethyl-indenyl, 2,4,7-trimethyl-indenyl, 4,5,6,7-tetrahydroindenyl, 2-methyl-4,5,6,7-tetrahydroindenyl, 4,7-dimethyl-4,5,6,7-tetrahydroindenyl, 2,4,7-trimethyl-4,5,6,7-tetrahydroindenyl and fluorenyl groups; and R^2 is $(CH_3)_2Si<$ or $-CH_2CH_2-$.
13. The catalyst according to any of claims 1 to 12 wherein, in said cyclopentadienyl compound of formula (I), the substituents Q are chlorine atoms or methyl groups.

14. A process for the homopolymerization or copolymerization of α -olefins, optionally in the presence of polyenes and/or cycloolefins, characterised by being carried out in the presence of a catalyst as described in any of claims 1 to 13.
15. The process according to claim 14, wherein said α -olefin is ethylene and said component (B) is a mixture of the two organometallic aluminium compounds of formula (II) wherein $z=0$ and $z=1$, in such amounts that the molar ratio between the hydrogen atoms directly bound to aluminium and aluminium atoms ranges from 0.02 to 0.3.
16. The process according to claim 15, wherein in step (i), said the molar ratio between the hydrogen atoms directly bound to aluminium and aluminium atoms is higher than 0.02 in step (i), and is lower than 0.2 in step (ii).
17. The process according to claim 14, wherein said α -olefin is propylene and said component (B) is a mixture of the two organometallic aluminium compounds of formula (II) wherein $z=0$ and $z=1$, in such amounts that the molar ratio between the hydrogen atoms directly bound to aluminium and aluminium atoms ranges from 0.02 to 0.3.
18. The process according to claim 18, wherein said molar ratio between the hydrogen atoms directly bound to aluminium and aluminium atoms is higher than 0.02 in step (i), and is lower than 0.4 in step (ii).
20. A process for preparing a catalyst for the polymerisation of olefins as described in any of claims 1-13, comprising the following steps:

- (i) contacting component (A) with part of component (B) in the absence of component (C), wherein said components (A), (B) and (C) have the meaning reported in claim 1;
 - (ii) contacting part of component (B) with component (C) in the absence of component (A); and successively
 - (iii) contacting the products obtained in steps (i) and (ii);
- wherein said components (B) used in steps (i) and (ii) can be the same or different from each other.

INTERNATIONAL SEARCH REPORT

Inter Application No

PCT/EP 98/06733

A. CLASSIFICATION OF SUBJECT MATTER
IPC 6 C08F4/642 C08F10/00

According to International Patent Classification (IPC) or to both national classification and IPC

B. FIELDS SEARCHED

Minimum documentation searched (classification system followed by classification symbols)

IPC 6 C08F

Documentation searched other than minimum documentation to the extent that such documents are included in the fields searched

Electronic data base consulted during the international search (name of data base and, where practical, search terms used)

C. DOCUMENTS CONSIDERED TO BE RELEVANT

Category *	Citation of document, with indication, where appropriate, of the relevant passages	Relevant to claim No.
X	EP 0 368 644 A (EXXON CHEMICAL PATENTS INC) 16 May 1990	1, 10, 13, 14, 20
Y	see example 1	2, 3, 8, 11, 12
	see example 8	
	see claim 1	
X	see claim 3	9
	see page 9, line 42 - line 51	
Y	WO 96 02580 A (MONTELL TECHNOLOGY COMPANY BV) 1 February 1996	2, 3, 8, 11, 12
	cited in the application	
	see claims 1, 2, 5, 6, 8	
X	EP 0 539 876 A (ETHYL CORP) 5 May 1993	1, 13, 20
	see example 1	
	see page 5, line 22	
A	see example 12	6
	--- -/-	

☒ Further documents are listed in the continuation of box C.

☒ Patent family members are listed in annex.

* Special categories of cited documents:

"A" document defining the general state of the art which is not considered to be of particular relevance

"E" earlier document but published on or after the international filing date

"L" document which may throw doubts on priority claim(s) or which is cited to establish the publication date of another citation or other special reason (as specified)

"O" document referring to an oral disclosure, use, exhibition or other means

"P" document published prior to the international filing date but later than the priority date claimed

"T" later document published after the international filing date or priority date and not in conflict with the application but cited to understand the principle or theory underlying the invention

"X" document of particular relevance; the claimed invention cannot be considered novel or cannot be considered to involve an inventive step when the document is taken alone

"Y" document of particular relevance; the claimed invention cannot be considered to involve an inventive step when the document is combined with one or more other such documents, such combination being obvious to a person skilled in the art.

"S" document member of the same patent family

Date of the actual completion of the international search

25 February 1999

Date of mailing of the international search report

15/03/1999

Name and mailing address of the ISA

European Patent Office, P.B. 5818 Patentlaan 2
NL - 2280 HV Rijswijk
Tel. (+31-70) 340-2040, Tx. 31 651 epo nl,
Fax: (+31-70) 340-3016

Authorized officer

Fischer, B

INTERNATIONAL SEARCH REPORT

International Application No.

PCT/EP 98/06733

C.(Continuation) DOCUMENTS CONSIDERED TO BE RELEVANT

Category	Citation of document, with indication, where appropriate, of the relevant passages	Relevant to claim No.
X	<p>EP 0 563 834 A (MITSUI TOATSU CHEMICALS) 6 October 1993 see example 1</p> <p>-----</p>	<p>1, 10, 13, 14, 20</p>

INTERNATIONAL SEARCH REPORT

Information on patent family members

International Application No.

PCT/EP 8/06733

Patent document cited in search report	Publication date	Patent family member(s)	Publication date
EP 0368644 A	16-05-1990	US 4925821 A	15-05-1990
		AT 148893 T	15-02-1997
		AU 621172 B	05-03-1992
		AU 4624889 A	28-05-1990
		CA 2002436 A	08-05-1990
		DE 68927765 D	27-03-1997
		DE 68927765 T	28-05-1997
		DK 163790 A	23-08-1990
		ES 2097743 T	16-04-1997
		JP 3502210 T	23-05-1991
		PT 92233 A	31-05-1990
		WO 9005149 A	17-05-1990
WO 9602580 A	01-02-1996	IT 1273661 B	09-07-1997
		AT 163653 T	15-03-1998
		AU 695214 B	06-08-1998
		AU 3113595 A	16-02-1996
		BG 100514 A	31-01-1997
		BR 9506295 A	12-08-1997
		CN 1135761 A	13-11-1996
		CZ 9601127 A	11-12-1996
		DE 69501720 D	09-04-1998
		DE 69501720 T	10-09-1998
		EP 0720627 A	10-07-1996
		ES 2115391 T	16-06-1998
		FI 961269 A	02-05-1996
		HU 74321 A, B	30-12-1996
		JP 9503251 T	31-03-1997
		NO 961109 A	15-05-1996
		PL 313588 A	08-07-1996
		SK 49496 A	05-03-1997
		US 5849653 A	15-12-1998
		ZA 9505988 A	18-06-1996
EP 0539876 A	05-05-1993	US 5210338 A	11-05-1993
		CA 2080102 A	26-04-1993
		DE 69207551 D	22-02-1996
		DE 69207551 T	15-05-1996
		JP 5239070 A	17-09-1993
EP 0563834 A	06-10-1993	DE 69300609 D	16-11-1995
		DE 69300609 T	13-06-1996
		JP 6041235 A	15-02-1994
		KR 9513680 B	13-11-1995
		US 5677409 A	14-10-1997
		US 5658999 A	19-08-1997

